

Technical Data Sheet

- Thickness 4mm
- Mineral Slate Finish
- APP Bituminous Membrane
- Extremely flexible
- Excellent adhesion
- Watertight
- Tear resistant
- Non Toxic
- Balconies
- Roof Tops
- Podiums

Pasco Construction Solutions P/L
13 – 15 Brighton Street
Richmond Vic 3121
Ph: 03 9429 9111
Fax: 03 9429 6111
www.pasco.net.au

Aquaproof 4M

4mm Mineral Slate Finish, APP Torch Applied Membrane

Description

Aquaproof 4M is a high quality, slate mineral finished torch applied bituminous sheet waterproofing membrane with a non-woven spunbound polyester carrier. This combination gives **Aquaproof 4M** excellent tensile strength and tear resistance, suitable for a variety of waterproofing applications.

Features/Benefits

- Excellent UV Resistance
- High tensile Strength
- Excellent adhesion
- Suitable for low temperature
- Excellent elongation
- Watertight
- Tear resistant
- Uniform thickness

Uses

- Roof-tops
- Podiums
- Terraces
- Balconies

APPLICATION INSTRUCTIONS

Substrate preparation

- All surfaces must be structurally sound and free of dirt, dust, grease, paint, oil, form release, curing agents and other contaminants.
- All protrusions are to be removed and all voids, cracks, joints etc. filled prior to membrane application.
- Ensure substrate has adequate falls i.e. 1:100 for balconies podiums.

Aquaproof 4M

Application

1. Installation shall be in accordance with the manufacturers recommendations.
2. Prime all surfaces using Aquaprime WB Bitumen Primer and allow to dry. Coverage depends on substrate porosity.
3. Install a 50 x 50mm sand/cement coving to all internal horizontal corners.
4. **First Layer Aquaproof 3** is fully bonded to the substrate with 100mm side laps and 150mm end laps. All laps are to be sealed using a gas torch.
5. **Second Layer Aquaproof 4M** is fully bonded to **Aquaproof 3** with 75mm side laps and 100mm end laps. All laps are to be sealed using a gas torch.
6. Please contact Pasco to discuss individual specifications for your project/application as **Aquaproof 4M** can be used in various applications.

Precautions

- Ensure sheet flooring is appropriately fixed as per manufacturers' instructions.

Coverage

- 10m² not including side and end laps.

Clean Up

Cured material may be removed by mechanical means and the use of Pasco Xylene.

Packaging

Roll size: 1m x 10m

Storage

Aquaproof 4M should be stored in an upright position.

Health and Safety

Wear suitable protective clothing, gloves and eye/face protection. Use only in well ventilated areas.

In case of contact with eyes, rinse immediately with plenty of water and contact a Doctor or Poisons Information Centre (**Ph 13 11 26**). In case of skin contact, wash affected area with hand cleaner followed by soap and water.

Material Safety Data Sheets must be read and understood prior to using product.

Technical Specifications		
Property	Test method	Result
Roll length	TS EN 1849-2	10m
Roll width	TS EN 1849-2	1m
Membrane thickness	TS EN 1849-2	4mm
Reinforcement type	-	Non-Woven Polyester
Reinforcement weight		180 Gr/m ²
Softening point	ASTM D36	>150°C
Penetration at 25°C	ASTM D5	20-30dmm
Flow resistance	TS EN 1110	120°C
Tensile strength		
Longitudinal	EN 12311-1	850 N/5cm
Transversal		650 N/5cm
Membrane elongation		
Longitudinal	EN 12311-1	40%
Transversal		45%
Tearing strength		
Longitudinal	EN 12310-1	180 N
Transversal		120 N
Puncture resistance		
Static	EN 12730:2001	L ₄
Dynamic		I ₄

Pasco Construction Solutions Pty Ltd warrants its' products to be free of defects and faulty manufacture and are sold subject to its standard terms and conditions of sale, which are available upon request. All endeavors have been made to ensure the information provided in this technical data sheet is accurate and correct, however as the use of this material is beyond the supplier's control, liability is limited to replacement of material proven faulty. It is the responsibility of the purchaser to ensure that the product is suitable for the specific application and that it is applied in accordance with the suppliers recommendations.

PASCO